


Mex-Fix C1, made from martensitic stainless steel C1, is a screw specifically developed for fastening facade profiles to wooden substructures.

long service life and reliable

performance

The screw features a rounded head, milling and driving threads, a specially designed tip, a Torx profile, and many other advantages.

Description and Benefits of the Mex-Fix C1



Material Description - Stainless Steel C1

- Suitable for softwood species and woods with low tannin content, such as pine, spruce, larch, etc.
- Surface treatment by passivation increases corrosion protection
- ✓ High durability: C1 is martensitic stainless steel, hardened, and has 50% higher breakaway torque than austenitic stainless steel A2 and A4
- ✓ **Limited corrosion resistance:** Stainless steel C1 is not suitable for use in aggressive environments, such as areas with high salt or chlorine content
- Magnetic properties











Mex-Fix C1 is intended for:



Softwood species

- ✓ Spruce
- ✓ Siberian Larch*
- ✓ Silesian Larch*
- ✓ Pine (with and without pressure treatment)

Note: This recommendation may not apply to all usage scenarios. The properties and lifespan of the screw can be influenced by specific environmental conditions. Therefore, we recommend consulting with your dealer.

* It is possible to use, but we recommend consulting with your dealer.

Mex® FIX-C1

Cladding Screw Offer

Art. No.	Screw Name	Size Torx		Packaging	
440C1FIX	Mex-Fix-C1	4,0x40 mm	TX15	200 pcs	
450C1FIX	Mex-Fix-C1	4,0x50 mm	TX15	200 pcs	
460C1FIX	Mex-Fix-C1	4,0x60 mm	TX15	200 pcs	
4550C1FIX	Mex-Fix-C1	4,5x50 mm	TX20	200 pcs	
4560C1FIX	Mex-Fix-C1	4,5x60 mm	TX20	200 pcs	
4570C1FIX	Mex-Fix-C1	4,5x70 mm	TX20	200 pcs	
545C1FIX	Mex-Fix-C1	5,0x45 mm	TX20	200 pcs	
550C1FIX	Mex-Fix-C1	5,0x50 mm	TX20	200 pcs	
560C1FIX	Mex-Fix-C1	5,0x60 mm	TX20	200 pcs	
570C1FIX	Mex-Fix-C1	5,0x70 mm	TX20	200 pcs	
580C1FIX	Mex-Fix-C1	5,0x80 mm	TX20	200 pcs	


Assessment of screw properties

Product	Characteristic yield moment $M_{y,k}$ [Nmm]	Characteristic withdrawal parameter $f_{ax,k}$ [N/mm²]		Characteristic head pull-through	Characteristic tensile capacity	Characteristic torsional ratio	
		perpendicular to the grain	parallel to the grain	parameter $f_{head,k}[N/mm^2]$	f _{tens,k} [kN]x	torsional ratio	
Mex-Fix-C1 ø 4,5 mm	4,626	16,47	13,20	22,75	6,97	3,86	
Characteristic density of wood [kg/m³]	_	350		350	_	450	
Durability (i.e. corrosion protection)	Stainless steel SS 410 (Service class 3 acc. to EN 1995-1-1)						

During installation, it is recommended to pre-drill holes for the screws to ensure accuracy and reduce the risk of material damage.



With Pre-drilling



Without Pre-drilling